



Confidentiality Disclaimer:

This document and the technology disclosed thereby is owned by Argent International, Inc. It contains confidential proprietary and/or trade secret information and must not be copied. The document and the information it contains must be used only by the recipient for the specific use for which it was requested. This document and all copies of it must be returned immediately upon the request to do so by Argent International, Inc

APPLICATION DATA SHEET

Note: If more information is needed please call for a technical data sheet.

PRODUCT: Polyethylene Film Tape

PRODUCT DESCRIPTION: Polyethylene film tape is a single coated clear polyethylene film with 5 mils of an acrylic pressure sensitive adhesive. It is supplied on a 50# tan kraft release liner. For a low cost alternative to molded rubber and plastic hole-plugs, Polyethylene film tape is your solution. Constructed of flexible low-density polyethylene film, and a very tacky, high-performance acrylic adhesive system, it is ideal for use on smaller holes where strength and flexibility are application requirements. Polyethylene film tape can easily wrap around corners and conform to complex surfaces, enabling it to excel where rigid materials or molded plugs just are not effective.

CONSTRUCTION:

Substrate (clear LDPE)	6.0 mils
Adhesive Thickness	5.0 mils
Total Thickness	14.0 mils

PERFORMANCE:

Peel Adhesion:

Initial: 20 min @ RT	170 oz / in
----------------------	-------------

Holding Power:

2.2 psi (1" x 1" x 1000g) @ RT	16 hours
--------------------------------	----------

Notice: All statements, information and data given herein are believed to be accurate and reliable. These values are intended as guides only and not as specification limits. This data is presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may or may not be required.