

**Confidentiality Disclaimer:**

This document and the technology disclosed thereby is owned by Argent International, Inc.. It contains confidential proprietary and/ or trade secret information and must not be copied. The document and the information it contains must be used only by the recipient for the specific use for which it was requested. This document and all copies of it must be returned immediately upon request to do so by Argent International, Inc.

APPLICATION DATA SHEET**PRODUCT: 1.5lb Ether**

Test	Minimum	Maximum	Results	Units
Density	1.56		1.52	lbs/ft3
Tensile Strength	11.6		15.6	psi
Elongation	160		150	%
Tear Strength	1.6		2.1	lbs/in
CFD (4x4x2)			0.56	psi
CFD (4x4x2) Heat Age		25	7	%
CFD (4x4x2) Autoclave		30	7	%
Compression Set, 50%		8	3.5	%
Comp. Set, 50% Autoclave		30	3	%
Flammability (MVSS 302)		4	0 / SE	in/minute
Odor		2	2	-
Fogging (No film or droplets)	60		89	-
Sound Absorption	Pass		Pass	-
Ash Content		1	0.6	%
Staining	None		None	-

Notice: All statements, information and data given herein are believed to be accurate and reliable. These values are intended as guides only and not as specification limits. This data is presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may or may not be required.