



### Confidentiality Disclaimer:

This document and the technology disclosed thereby is owned by Argent International, Inc., It contains confidential proprietary and/ or trade secret information and must not be copied. The document and the information it contains must be used only by the recipient for the specific use for which it was requested. This document and all copies of it must be returned immediately upon request to do so by Argent International, Inc.

## APPLICATION DATA SHEET

**PRODUCT: 6lb Ester**

Test	Minimum	Maximum	Results	Units
Density	5.5	6	5.85	lbs/ft3
Tensile Strength	15		39.9	psi
Elongation	200		513	%
Tear Strength	2.5		5.2	lbs/in
25% CFD (4" x 4" x 2")	12	20	16.3	lbs
50% Compression Set		15	2.7	%
Odor	No Offensive Odor		No Offensive Odor	-
Low T Flexibility	No Cracking		No Cracking	-
Cell Structure	Homogenous		Homogenous	-
Resistance to Deterioration	No Cracking		None	-

**Notice:** All statements, information and data given herein are believed to be accurate and reliable. These values are intended as guides only and not as specification limits. This data is presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may or may not be required.