Confidentiality Disclaimer:

This document and the technology disclosed thereby is owned by Argent International, Inc. It contains confidential proprietary and/or trade secret information and must not be copied. The document and the information it contains must be used only by the recipient for the specific use for which it was requested. This document and all copies of it must be returned immediately upon the request to do so by Argent International, Inc

APPLICATION DATA SHEET

Note: If more information is needed please call for a technical data sheet.

PRODUCT: ARV2125 - Felt Tape

PRODUCT DESCRIPTION: ARV2125 Felt Tape is designed to be used for BSR (buzz, squeak, & rattle) applications that require both anti-squeak and anti-rattle capabilities. This 75% wool felt composite meets SAE commercial standard grade. High-strength adhesive is laminated to it to create a durable and extremely capable BSR tape.

PROPERTIES	
Felt	Wool Content
Abrasion Resistance	good
Standard Thickness Range/in.	1/16 to 3/32
Color	Gray / Black
Temperature Range, F	-80 to 200

PRODUCT: Acrylic Adhesive

TYPICAL ADHESION CHART

	Adhesive Transfer Tape	15 Minute Room Temp.		72 Hour Room Temp.	
		Oz. / In.	N/100 mm	Oz. / In.	N/100 mm
Stainless Steel	Adhesive	109	119	140	153
ABS	Adhesive	102	112	128	140
Polypropylene	Adhesive	115	126	136	149

- **Humidity Resistance:** Excellent
- **U.V. Resistance:** Excellent
- **Temperature Cycling Resistance:** High bond strength is maintained after cycling four times through: 4 Hours at 158°F (70°C) / 4 Hours at -20°F (-29°C) / 4 Hours at 73°F (22°C)
- **Chemical Resistance:** Excellent
- **Temperature Resistance:** Adhesive is usable for short periods (minutes, hours) at room temperatures up to 300°F (148°C) and for intermittent longer periods of time (days, weeks) up to 200°F (93°C).
- **Lower Service Temperature:** -40°F (-40°C).

Notice: All statements, information and data given herein are believed to be accurate and reliable. These values are intended as guides only intended as guides only and not as specification limits. This data is presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may or may not be required.

Argent International, Inc. • 41016 Concept Drive • Plymouth, Michigan • 48170
Phone: (800) 223-9890 • Fax: (734) 582-9999 • www.argent-international.com