

**Confidentiality Disclaimer:**

This document and the technology disclosed thereby is owned by Argent International, Inc. It contains confidential proprietary and/or trade secret information and must not be copied. The document and the information it contains must be used only by the recipient for the specific use for which it was requested. This document and all copies of it must be returned immediately upon the request to do so by Argent International, Inc

APPLICATION DATA SHEET

Note: more information is needed please call for a technical data sheet.

PRODUCT: ARV2210 - Non-Woven Felt w/ PSA

PRODUCT DESCRIPTION: Non-Woven Flexibility and thinness are the key attributes of Non-Woven, which make it well suited to applications that require both moderate abrasion resistance and conformability. Non-Woven tape may be supplied with a variety of adhesive systems depending on the specific performance requirements of a given BSR issue. Typical applications might include use as a slip barrier between polystyrene, metal, or plastic components.

MATERIAL: Drylaid, spunlaced chemically bonded nonwoven

COLOR: Black

WEIGHT, g/m² : 65±11

FLAME RETARDANT: < 100

TEST METHOD: FMVSS 302

PRODUCT: Low Fogging Adhesive Transfer Tape

Note: The adhesive system of this composite can be customized for maximum performance to the individual application requirements.

ADHESIVE: 5.0 mils #300MP Acrylic Adhesive

TYPICAL PHYSICAL PROPERTIES AND PERFORMANCE CHARACTERISTICS:

Surface	15 Minute Dwell		72 Hour Dwell		72 Hour Dwell @ 158°F	
	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm
Stainless Steel	102	112	131	143	166	182
	NA	NA	93	102	78	85

ENVIRONMENTAL PERFORMANCE:

Temperature Resistance: Short Term: 250°F (121°C).

Humidity Resistance: No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C).

Notice: All statements, information and data given herein are believed to be accurate and reliable. These values are intended as guides only and not as specification limits. This data is presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may or may not be required.