Confidentiality Disclaimer:

This document and the technology disclosed thereby is owned by Argent International, Inc. It contains confidential proprietary and/or trade secret information and must not be copied. The document and the information it contains must be used only by the recipient for the specific use for which it was requested. This document and all copies of it must be returned immediately upon the request to do so by Argent International, Inc

APPLICATION DATA SHEET

Note: If more information is needed please call for a technical data sheet.

PRODUCT: ARV3065 - Series 30 Very Soft, Urethane Foam Tape w/ PSA

PRODUCT DESCRIPTION: Typical uses for foam tape include BSR applications that require both sound dampening and moderate abrasion resistance. Foam tape is often used to span larger gaps between mating components, such as in a headliner assembly. Available in a variety of types, densities, thicknesses, and custom high-performance adhesive systems, foam tape is highly versatile. For applications requiring additional abrasion resistance, films may be laminated to the composite.

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Standard Color (code)		Black (04)
Compression Set, % max.	Test D @ 73° F (23°C)	2
	Test D @ 158° F (70°C)	10
	Autoclaved 5hrs @ 250°F (121°C)	5
TEMPERATURE RESISTANCE		
Recommended Constant Use, max.		194°F (90°C)
Recommended Intermittent Use, max.		250°F (121°C)
FLAMMABILITY AND OUTGASSING		
Flammability	MVSS 302 (Pass ≥)	

PRODUCT: Low Fogging Adhesive Transfer Tape

Note: The adhesive system of this composite can be customized for maximum performance to the individual application requirements.

ADHESIVE: 5.0 mils #300MP Acrylic Adhesive

TYPICAL PHYSICAL PROPERTIES AND PERFORMANCE CHARACTERISTICS:

	15 Minute Dwell		72 Hour Dwell		72 Hour Dwell @ 158°F	
Surface	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	102	112	131	143	166	182
ABS	NA	NA	93	102	78	85

ENVIRONMENTAL PERFORMANCE:

Temperature Resistance: Short Term: 250°F (121°C).

Humidity Resistance: No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C).

Notice: All statements, information and data given herein are believed to be accurate and reliable. These values are intended as guides only and not as specification limits. This data is presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may or may not be required.

Argent International, Inc. • 41016 Concept Drive • Plymouth, Michigan • 48170
Phone: (800) 223-9890 • Fax: (734) 582-9999 • www.argent-international.com