Argent

poron® ALWAYS THERE

PORON® 4701-V0-M Medium

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, kg/m^3 (lb./ft^3)	ASTM D 3574-95, Test A	400 (25)
Tolerance, %		± 10
Thickness, mm (inches)		5 (0.197) 6 (0.236)
Tolerance, %		± 10
Standard Color (Code)		Smoke Gray (107)
Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min) Strain Rate Force Measured @ 25% Deflection	41 - 110 (6 - 16)
Hardness, Durometer Shore OO	ASTM D2240-97	24
Compression Set, % max	ASTM D3574-95 Test D @ 23°C (73°F) ASTM D3574-95 Test D @ 70°C (158°F)	5 10
Tensile Strength, min. kPa (psi)	ASTM D3574-75 Test E	580 (84)
Tensile Elongation, % min.	ASTM D3574-75 Test E	55

ROGERS CORPORATION

The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2013, 2014, 2018, 2023 Rogers Corporation. All rights reserved. 0723-PDF • Publication #17-277 www.rogerscorp.com