Rubberlite Incorporated

Argent

Typical Properties of

RE43E

Polymer	EPDM Blend		
ASTM D1056 Classification	2A3		
ASTM D1056 Suffix Compliances	A2, B2, C1, C2, C3, F1, M		
ASTM D6576 Classification	Type II A,B Medium		
Physical Property	**Test Method**	**Result (US Units)**	**Result (Metric Units)**
Density	ASTM D1056	7 -11 pcf	112.1 – 176.2 kg/m^3
Compression Deflection 25%	ASTM D1056	9 – 13 psi	62 – 89.6 kPa
Compression Set 50%	ASTM D1056	25% Max	25% Max
Water Absorption	ASTM D1056	5% Max	5% Max
Tensile Strength	ASTM D412	151 psi	1041.1 kPa
Elongation	ASTM D412	160 %	160 %
Tear Strenth	ASTM D624	25.7 lb/in	4.5 kN/m
CD after Oven Aging	ASTM D1056	30% Max	30% Max
Flammability	FMVSS-302	Pass @ .040" or Thicker	
Service Temperature	-40 to 250 F		

Contact customer service for specification inquiries.

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.